



Two Pack Epoxy Water Based Floor Paint

DESCRIPTION

Johnstone's Trade 2 Pack Epoxy Water Based Floor Paint is a high performance, semi-gloss coating which provides a Non-flammable, low odour, highly resilient film. Ideal for use on floors and primed steelwork where high durability is required. To boost the slip resistance of the product, use with Johnstone's Trade Anti-Slip Additive.

INSTRUCTIONS: THIS IS THE BASE PACK OF A 2 PACK PRODUCT. THE CORRECT AMOUNT OF ACTIVATOR IS CONTAINED IN THE SMALLER TIN AND MUST BE ADDED AND MIXED THOROUGHLY BEFORE USE. THE MIXTURE MUST BE USED WITHIN 1 HOURS. PARTLY USED CONTAINERS MUST NOT BE RESEALED AFTER USE DUE TO PRESSURE BUILD UP.

RECOMMENDED USES



Floors and primed steelwork where low odour, high durability and good chemical resistance are required.

SPECIAL PROPERTIES

Non flammable, low odour with a highly resilient film.

COLOUR RANGE

Dark Green (14C39); Princess Grey (00A05); Dark Grey (18B25); Morning Mist (10A03); Tile Red.

FINISH

Semi-gloss.

VOLUME SOLID

50%

COVERAGE



Johnstone's Trade 2 Pack Epoxy Water Based Floor Paint will cover at a rate of approximately 5-7 square metres per litre, depending on the nature and porosity of the surface.

FILM THICKNESS

Wet: 120µm, dry: 60µm.

DRYING TIME



Touch dry in 4 hours. Recoatable after 24 hours. Fully cured after 7 days.

TRANSPORTATION & STORAGE

To avoid the risk of spillage, always store and transport in a secure upright position. PROTECT FROM FROST.

THINNER

Thinner: Water - only while the product is wet.

VOC CONTENT

EU limit value for this product (Cat A/j): 140g/l (2010). This product contains max 3g/l VOC.



KEY PROPERTIES

- High performance, semi-gloss finish
- Abrasion resistance
- High durability and chemical resistance

PREPARATION

All surfaces to be painted should be sound, clean, dry and free from dust and other contaminants, in particular oil, grease, curing compounds, release agents, chalk, mildew and loose or flaking material. If the floor has been power floated, use Johnstone's Trade Acid Etch Solution to provide a key. Ensure the surface is completely dry prior to application. It is important to ensure that the concrete/cement is fully cured before the paint is applied. For more information and free Johnstone's Trade datasheets, call 01924 354354 or visit www.johnstonestrade.com

APPLICATION



Ensure good ventilation during application and drying. The base and activator should be mixed together at a ratio of 4/1 by volume - ensure that the components are completely mixed before application. A first coat thinned with 10% water is recommended on bare concrete. The mixture must be used within 1 hours of mixing. Suitable for application by brush or roller. Always follow the 3 step system unless you have received a Johnstone's Trade technical specification that recommends an alternative.

CLEANING



Remove as much product as possible from application equipment before cleaning. Clean equipment immediately after use with warm soapy water and rinse thoroughly. Mixed, part used containers must not be resealed after use, due to pressure build up. Do not empty product into drains or watercourses.

PRECAUTIONS

- Keep out of reach of children
- Avoid contact with skin and eyes
- Do not ingest
- If medical advice is needed have container or label to hand
- Please refer to Product Label & Safety Data Sheet (SDS) for hazard warnings and information on safe handling/use/transport/storage/disposal/emergency
- SDS available : www.johnstonestrade.com or call 01924 354354

SIZE

5 Litre (4L Base + 1L Activator).



For more information on our products and services call 01924 354354 or visit www.johnstonestrade.com.