# 510

(~ %) <sup>70</sup> <sup>%</sup>/<sub>%</sub> ↓

**↑** 

€+12°C

## **Technical Data Sheet** StoSilent Board 310 F

Acoustic panel made of expanded glass granulate for suspended ceiling and wall structures

Area of application	interior
	<ul> <li>for suspended ceiling and wall structures</li> </ul>
	<ul> <li>for the StoSilent Distance Flex acoustic system</li> </ul>
	<ul> <li>for structures with increased requirements on mechanical resistance as well as</li> </ul>
	for bent constructions (radius $> 5 \text{ m}$ )
	<ul> <li>fixing with screws, bonded board joints</li> </ul>
Properties	• up to 200 m <sup>2</sup> possible without expansion joint (max. side length: 20 m)
	<ul> <li>reduction in the reverberation time and noise level</li> </ul>
	<ul> <li>improved ability to concentrate</li> </ul>
	$\bullet$ weighted sound absorption coefficient $\alpha$ $_{W}$ of up to 0.45 depending on the
	suspension height
	<ul> <li>low weight and high stiffness</li> </ul>
	<ul> <li>low moisture-induced and thermal expansion</li> </ul>
Format	board edge: sharp-edged / coated
	<ul> <li>length x width x thickness</li> </ul>
	• 2400 x 1200 x 15 mm
Appearance	textured surface
	<ul> <li>fine graining with the StoSilent Decor M or StoSilent Decor MF finish</li> </ul>
Information/notes	<ul> <li>use in brine or saltwater swimming pools only on request</li> </ul>
	<ul> <li>not suitable in splash water zones</li> </ul>

CE

#### **Technical data**

Criterion	Standard / test specification	Value/ Unit	Notes
Diffusion-equivalent air layer thickness	EN ISO 7783	0.10 m	with coating
Reaction to fire (class)	EN 13501-1	B-s1, d0	with coating

• observe installation instructions



	Rated value of thermal conductivity $\lambda$	TIAP-655 based on EN 12667	0.08 W/(m*K)	with coating		
	Mass per unit area		5.0 kg/m²			
	Bulk density		380 kg/m³			
	Sound absorption coefficient c		0.45	With coating; can vary depending on the suspension height and damping		
	the natural raw materials in	The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.				
Substrate						
Requirements	The substrate must be firm	, dry, clean, and load-	bearing.			
Application						
	Lowoot substrate and and	notion tomporature:	12 °C at may 70	% relative air		
Application temperature	Lowest substrate and appli- humidity; installation after a Rapid shock-type heating of formation.	djusting the equilibriu	m humidity in the	e room.		
Application temperature	humidity; installation after a Rapid shock-type heating c	djusting the equilibriu	m humidity in the lation and drying	e room.		
Application temperature	humidity; installation after a Rapid shock-type heating c formation.	djusting the equilibriu	m humidity in the lation and drying	e room. can induce crac		
Application temperature	humidity; installation after a Rapid shock-type heating c formation.	djusting the equilibriu r cooling during instal	m humidity in the lation and drying Approx. co 1.00 ed as a guide. If	e room. can induce crac onsumption m²/m² required, precise		
Application temperature	humidity; installation after a Rapid shock-type heating c formation. Type The stated consumption va	djusting the equilibriu or cooling during install lues are only to be use uttings should be deter ccordance with EN 13	m humidity in the lation and drying Approx. co 1.00 ed as a guide. If rmined on the pro	e room. can induce crac onsumption m²/m² required, precise oject.		
Application temperature Consumption	humidity; installation after a Rapid shock-type heating of formation. Type The stated consumption va consumption values plus of metal sub-construction in a	djusting the equilibriu or cooling during install lues are only to be use uttings should be deter ccordance with EN 13	m humidity in the lation and drying Approx. co 1.00 ed as a guide. If rmined on the pro	e room. can induce crac onsumption m²/m² required, precise oject.		
Application temperature	humidity; installation after a Rapid shock-type heating of formation. Type The stated consumption va consumption values plus of metal sub-construction in a grid bonded with StoSilent	djusting the equilibriu or cooling during install lues are only to be use uttings should be deter ccordance with EN 13 Profile Tape	m humidity in the lation and drying Approx. co 1.00 ed as a guide. If rmined on the pro	e room. can induce crac onsumption m²/m² required, precise oject.		
Application temperature Consumption	humidity; installation after a Rapid shock-type heating of formation. Type The stated consumption va consumption values plus of metal sub-construction in a grid bonded with StoSilent StoSilent Board 310 F System adhesive:	djusting the equilibriu or cooling during install lues are only to be use uttings should be deter ccordance with EN 13 Profile Tape	m humidity in the lation and drying Approx. co 1.00 ed as a guide. If rmined on the pro	e room. can induce crac onsumption m²/m² required, precise oject.		
Application temperature Consumption	humidity; installation after a Rapid shock-type heating of formation. Type The stated consumption va consumption values plus of metal sub-construction in a grid bonded with StoSilent StoSilent Board 310 F System adhesive: StoSilent Fix(approx. 0.3 kg System filler:	djusting the equilibrius r cooling during install lues are only to be use uttings should be deter ccordance with EN 13 Profile Tape g/m <sup>2</sup> )	m humidity in the lation and drying Approx. co 1.00 ed as a guide. If rmined on the pro 964 with vernier	e room. can induce crac onsumption m²/m² required, precise oject.		



	or
	finish StoSilent Decor M(three spray application cycles with a total of 2.7 kg/m²)
Application	The boards should be fixed in a longitudinal direction to the carrier profiles to which the StoSilent Profile Tape was applied. Align longitudinal joints toward the incidence of light. Install the boards with transverse joints that are offset by at least 400 mm. Fix the boards with phosphate-treated, quick-assembly screws with a needle point (TN form in accordance with DIN 18182) starting from the middle of the board or a corner in order to avoid compressions. When fixing the screws, press the board firmly onto the sub-construction. Insert the screws approx. 15 mm from the board edge and sink the screw heads to a depth of approx. 1 mm. Ensure a distance of 200 mm between the screws.
	The bonding edges must be free from dust. At the factory, a sealant is applied to the board edges to make them flow-proof. Dust off, paint, or waterproof all edges cut subsequently or on site using the system paint or system adhesive in order for the finished surface to appear homogeneous (closed pores, no visible expanded glass). Mix the system adhesive (StoSilent Fix) in accordance with the application guidelines. After fixing the board, apply the system adhesive to the edges (e.g. with a Japanese spatula or cartridge). Press the following board onto the fine grid of the sub-construction, then push it against the already installed boards and fix it with screws.
	Use an electrical keyhole saw, handsaw or surform to cut, grind or plane the material.
	System connections: to enable pressure equalisation between the ceiling cavity and the used space, ensure rear ventilation either through an open, all-around joint or openings in the ceiling. The proportion of the ceiling opening should account for at least 0.8 % of the ceiling surface area. In most cases, this is achieved by an open all-around joint of 2 cm.
	In glancing light the ceilings are not free from visible unevenness.
Cleaning the tools	Remove dust after use.
Notes, recommendations, special information,	Please observe the general Sto application guidelines for Sto acoustic panel systems. They are available from Sto SE & Co. KGaA.



miscellaneous				
	Installation/coating must o	Installation/coating must only be carried out after prior instruction.		
	5 ( 5	etrofitting ceiling installations) is cut through, create .Seal the cavities in adjacent walls to prevent low-		
	Recommendation: installat above a height of 2 m.	tion on walls outside areas subject to a risk of impact,		
	Structural expansion joints	s must be incorporated.		
Delivery				
Colour shade	visible side: white (approx. RAL 9010), rear side: grey (approx. RAL 7039)			
Packaging	pallet			
Storage				
Storage conditions	Store in dry and frost-free of it to loads or stress.	conditions. Product is sensitive to shock; do not subject		
Certificates/approvals				
	Declaration of conformity No. 2014-04	Acoustic products formulation identity/name change Certificate of conformity		

Identification	
Product group	Acoustic panel

Safety

Observe the Safety Data Sheet!



#### **Special notes**

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.

Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

Sto SE & Co. KGaA Ehrenbachstr. 1 79780 Stühlingen / Germany Phone: +49 7744 57-0 Fax: +49 7744 57-2178 Infoservice.export@sto.com www.sto.com